

EUROPEAN PATENT APPLICATION

Application number: 82111637.3

Int. Cl.³: **C 08 B 37/10, C 08 H 1/00,**
A 61 L 17/00

Date of filing: 15.12.82

Priority: 15.12.81 NL 8105656

Applicant: **CORDIS EUROPA N.V.**, Oosteinde 8,
NL-9301 LJ Roden (NL)

Date of publication of application: 22.06.83
Bulletin 83/25

Inventor: Feijen, Jan, Oude grensweg 96, NL-7552 GD
Hengelo (O.) (NL)
Inventor: Hennink, Wilhelmus E., Hengeveldebrink 462,
NL-7544 VB Enschede (O.) (NL)


Designated Contracting States: **DE FR GB IT**

Representative: **Weickmann, Heinrich, Dipl.-Ing. et al,**
Patentanwälte Dipl.-Ing. H. Weickmann Dipl.-Phys.Dr. K.
Fincke Dipl.-Ing. F.A. Weickmann Dipl.-Chem. B. Huber
Dr.-Ing. H. Liska Möhlstrasse 22,
D-8000 München 86 (DE)

Conjugates of anticoagulant and protein.

Conjugates are provided which are covalently bonded conjugates of an anticoagulant and protein that are prepared in the presence of a coupling agent that forms amide linkages between the anticoagulant and the protein. Such amide linking

coupling agents exclude highly toxic coupling agents such as CNBr. These conjugates are useful for enhancing the blood compatibility of certain surfaces of a prosthetic device, a surgical apparatus, or an extra-corporeal medical device.



SPECIFICATIONBackground and Description of the Invention

5 The invention relates to a process for the preparation of a conjugate of an anticoagulant such as heparin to a water soluble protein, typically human protein, by coupling the heparin to the protein in an aqueous medium and in the presence of a coupling agent.

10 In the article "Heparin Coupled to Albumin, Dextran and Ficoll; Influence on Blood Coagulation and Platelets and in vivo Duration", Thrombosis Research 7 (1975) 273-284, A.N. Teien et al, the authors report upon an investigation carried out by them which indicates that a heparin-albumin complex possess anti-coagulation and
15 aggregation effects equal to those of free heparin. The heparin-albumin complex involved in their investigation was prepared by adding CNBr to a solution containing dextran, effecting an activation of the dextran in order to bridge heparin to the albumin, after which the whole
20 is mixed with an aqueous solution of heparin and albumin. The heparin-albumin complexes so obtained are then lyophilized and stored in Veronal buffer and are incorporated in a stock solution containing 16 mg heparin per cm³, which assumes complete recovery of heparin. The complexes
25 thus formed possess a molecular weight distribution due to, inter alia, the heterogeneity of the commercial heparin preparations, which also exhibit a distribution of molecular weights. Using CNBr in such a process is undesirable because of the very high toxicity of CNBr.
30 Also, using CNBr in this manner does not form covalent amide linkages.

An object of the invention is an improved process for the preparation of conjugates of heparin to a human protein, such conjugates being suitable to treat a material
35 surface or substrate for the improvement of its blood compatibility, particularly regarding the prevention of

blood coagulation and damage of blood components.
When a substrate is coated with such a conjugate, its
blood compatibility is improved, and the conjugates of
this invention are advantageously applied to artificial
5 organs, implants, catheters, and other medical
prostheses which are contacted with blood.

According to this invention, the coupling agent
for forming the conjugates should form amide linkages
between an anticoagulant such as heparin and protein.
10 The preferred coupling agent in this regard is 1-ethyl-
3-dimethylaminopropyl carbodiimide (or EDC).

EDC has been found to provide the best and most
reproducible results, particularly when EDC is applied
as the coupling agent and when the coupling is carried
15 out in an aqueous solution of heparin and the protein.
Within the process according to the invention, the coupling
reaction between the carboxyl groups present in heparin
and ϵ -NH₂-groups of lysine residues present in the
protein, is a direct coupling between these groups, a
20 heparin intermediate product being formed wherein the
carboxyl groups are activated by EDC to active ester
groups, which activated carboxyl groups are in turn
reactive towards the amino groups of the protein.

In a further elaboration of the process
25 according to the invention that utilizes EDC, the heparin
and the protein are each provided dissolved in water; the
pH of the solution is adjusted to a value of not higher
than 5.5, preferably between about 5.0 and 5.5; an aqueous
solution of EDC is added batchwise while maintaining the
30 pH on a level of not higher than 5.5; the coupling reaction
is carried out in the reaction mixture while agitating it;
and the heparin-protein conjugate is recovered from the
reaction mixture.

Normally, the reaction is carried out at room
35 temperature. However, higher temperatures may be applied,

for example body temperature, and up to the denaturation temperature of the applied protein, typically up to about 60 degrees centigrade. Generally, the concentration of the components heparin and protein to be coupled can
5 be varied greatly in the aqueous solutions, and the ratio of these components to each other in the conjugate may be varied up to a certain level by varying the weight ratio of heparin to protein.

With further reference to the pH values of
10 this process, when the coupling reaction according to this invention uses EDC, if there is a failure to adjust and maintain the pH-value at or below a pH value of about 5.5, the rate of the reaction of heparin with EDC is very low because the concentration of
15 the protonated carbodiimide groups of EDC is too low. Coupling agents other than EDC may exhibit different upper pH limits.

If the pH is too low, there are two undesirable results; denaturation of the protein takes place, and the
20 sulphamate groups in the heparin will be transformed into amino groups. Therefore, it is preferred that the pH of the reaction mixture is adjusted to and maintained at a value that is equal to or greater than 5.0.

When heparin-protein conjugates are formed
25 according to the invention, the composition of the components to be coupled may be at various weight ratios during the coupling reaction. A typical preferred weight ratio for the amounts of heparin and protein used in the process is such that the mol ratio of heparin to protein
30 in the conjugate is about 1 to 1, although other weight ratios may be utilized so that heparin-protein conjugates are obtained at a different mol ratio. One characteristic to be avoided in this regard is to attempt to couple excessive heparin molecules onto the protein to the extent
35 that the conjugate is overly hydrophilic and will not

adsorb onto hydrophobic substrates. Heparin does not readily adsorb onto hydrophobic substrates, while a protein such as albumin does so readily adsorb and typically a mol ratio of heparin to albumin above 3 to 1 should be avoided.

5 Regarding the protein which is to be used as the reaction component, and which is a generally water soluble human protein, such may be a water soluble protein, suitable for coupling and appearing in blood, for example albumin, 10 fibrinogen, γ -globulin, and the like. Albumin is preferred because, of the human proteins, albumin has the highest concentration in human blood. Moreover, albumin exerts a strengthened inhibiting effect relative to the adhesion of blood platelets. These proteins may 15 be used as such or in crosslinked form, for example by crosslinking with an aldehyde, for example glutaraldehyde. Dependent on the protein component used, one should always experimentally determine the desired pH of the reaction mixture, particularly from the point of view of avoiding 20 undesirable denaturation of the particular protein used.

 With regard to the anticoagulant, for example, heparin fractions may be used which are separated from heparin by fractionating it on the basis of difference in molecular weight and/or affinity relative to anti-thrombin 25 III. Because it is generally known that, by fractionating heparin with immobilized anti-thrombin III, heparin fractions with high and low affinity may be obtained, the use of fractionated heparin offers the possibility to control the anti-thrombogenic activity of the heparin-protein 30 conjugate.

 After the coupling reaction has taken place, the reaction mixture contains not only the desired covalently bonded heparin-protein conjugate, but also free, that is to say non-reacted, protein and heparin. To isolate the 35 conjugate from the reaction mixture, after optionally

having subjected the mixture to a prepurification, for example by dialysing it to remove superfluous EDC, the mixture preferably is passed over a first sorption agent, which sorbs the heparin-protein conjugate, free protein and free heparin. Whereupon, by elution with eluent of increasing ionic strength, it is possible to first desorb the free protein and subsequently the heparinous compounds, and the eluate which contain the heparinous compounds are preferably then passed over a second sorption agent, by elution of which one separately desorbs the free heparin and the heparin-protein conjugate, respectively, and isolates the heparin-protein conjugate. Preferably such a first sorption agent would be an anion exchange synthetic resin material, and the second sorption agent would be a material with different affinity relative to the heparinous compounds.

The invention also relates to a process for the improvement of the blood compatibility of a material surface or substrate by coating it with heparin or with heparin analogues as is generally discussed in "Artificial Organs, Proceedings of a Seminar on the Clinical Applications of Membrane Oxygenators and Sorbent Based Systems", MacMillan Press Ltd., 1977. In chapter 26 thereof, at pages 235-247, J. Feijen under the title "Thrombogenesis Caused by Blood-Foreign Surface Interaction" discussed the developments in the field of the blood compatibility of material surfaces, particularly regarding the occurring protein adsorption, adhesion of blood platelets and activation of intrinsic coagulation.

Within the framework of improving the blood compatibility of a material surface by coating it with an anticoagulant such as heparin or heparin analogues, the invention is characterized in that a heparin/non-crosslinked conjugate, prepared by the process according to the invention described hereinabove, is adsorbed to a

hydrophobic or hydrophilic material surface, particularly to a hydrophobic material surface, in which case the protein moiety will be directed to the material surface and the heparin moiety in the blood.

5 In some applications and aspects of this invention, it is desired to minimize the desorption of the coated anticoagulant-protein conjugate by exchange with other plasma proteins. Such can be accomplished by cross-linking the protein moiety of the conjugate,
10 typically after the conjugate has been formed and coated onto the material surface or substrate.

Apart from adsorption for the improvement of the blood compatability of a material surface by coating it with heparin or heparin analogues, it is also possible to
15 prepare and provide anticoagulant protein conjugates according to the present invention which are chemically attached to the material surface or substrate. In this instance, the protein is considered as a so-called "spacer" group, while it is also possible to effect an eventual
20 crosslink-reaction of the protein moiety after the material surface is coated with the heparin-protein conjugate having a non-crosslinked protein moiety.

The improvement of the blood compatibility of a material surface by coating it with an anticoagulant such
25 as heparin or heparin analogues may also be effected by providing the material surface with a crosslinked protein layer, whereupon heparin is coupled to the protein by the application of EDC as the coupling agent. In the coating obtained with this embodiment of the invention, the coupling
30 takes place via the amino groups of the protein, and the protein may also be considered as a "spacer" group between the material surface and the heparin.

Depending upon the particular aspect of this invention needed to provide a desired result, the conjugates
35 may be generally firmly attached to the substrate surface,

usually in association with a cross-linking operation,
or they may be only adsorbed thereto. Adsorbed conjugates
will exhibit desorption to the extent that the conjugates
will become generally released such that the conjugates
5 will provide anticoagulation properties to the blood
flowing past the substrate. In effect, this aspect
of the invention provides controlled release of anticoagulant
properties, which can be valuable in connection with
treatments using extra-corporeal devices such as catheters,
10 in connection with pretreatment of prosthetic devices
such as artificial blood vessels where enhanced tissue
ingrowth is very advantageous, or in connection with
surgical apparatus such as oxygenators where only temporary
anticoagulation is needed. The rate and extent of such
15 desorption or controlled release of conjugates will depend
upon the particular conjugate, upon the hydrophobic or
hydrophilic nature of the substrate being coated, and
upon the rate of blood flow that contacts the substrate.

The invention will be further explained by the
20 following examples, in which albumin is applied as the
protein component.

EXAMPLE I

a) Preparation

In this example, the process is carried out at
25 room temperature. 770 mg of heparin and 2590 mg of human
serumalbumin were dissolved in 39 cm³ of water. By means
of 1.0 N HCl, the pH of this solution was adjusted to
between 5.0 and 5.5. During the addition, a white-flaky
precipitate is generated, which is dissolved after about
30 minutes. Thereupon, incremental batches of 1 cm³
EDC-solution (concentration 32.5 mg/cm³) were added.
Eight incremental batches were added at 30-minute intervals.
As necessary, the pH was maintained at between 5.0 and 5.5
by the addition of 1.0 N HCl or 1.0 N NaOH. After all of
35 the EDC was added, the pH of the solution was adjusted to

7.5 by means of 1.0 N NaOH, whereupon the solution was agitated during 20 hours at room temperature. Thereafter, the solution was dialyzed for 2 hours against a 25 mmol tris/HCl solution (pH 7.5) to remove superfluous EDC.

5

b) Isolation of the conjugate

In addition to the desired albumin-heparin conjugate, the reaction mixture also contained albumin and heparin which had not yet reacted. For the separation of these free components, use was made of an anion exchange column and an affinity column, i.e. a column provided with diethylaminoethyl-cellulose (DEAE-cellulose), followed by a column provided with Cibracron Blue Sepharose (CB-Sepharose). The dialyzed reaction mixture obtained in this manner was passed over a DEAE-cellulose column (5 mg material/cm³ gel) which was in equilibrium with 25 mmol tris/HCl at pH=7.5. Then, the column was eluted with ^{one} column volume ^{of} 25 mmol tris/HCl (pH 7.5). Thereupon the column was eluted with 1.5-2 times the column volume 150 mmol NaCl + 25 mmol tris/HCl (pH 7.5). At this step the ionic strength of the elution liquid was such that the "free" albumin which had not reacted was being separated from the column and eluted. Next, the DEAE-column was eluted with 1.5-2 times the column volume 500 mmol NaCl + 25 mmol tris/HCl (pH 7.5). At this ionic strength the heparin-albumin conjugate as well as the non-reacted "free" heparin was separated from the column. The fractions which were received through elution of the column with the solution containing 500 mmol NaCl, and which had an optical density at 280 nm (λ_{max} albumin) > 0.2, were combined and used for further purification with CB-Sepharose. The elution pattern of the DEAE-separation, as described above, is shown in Figure 1. The CB-Sepharose column was equilibrated with a 1% NaCl and 25 mmol tris/HCl (pH 7.5) solution, whereupon the combined fractions of the DEAE-column were passed over

- 9 -

the CB-Sepharose column. To remove the "free" heparin present in the solution, the column was eluted with 1 times the column volume 1% NaCl and 25 mmol tris/HCl (pH 7.5) solution. Thereupon, the albumin-heparin conjugate was eluted from the CB-column by means of a 1% NaCl + 25 mmol tris/HCl (pH 7.5) + 250 mmol KSCN solution. The fractions having an optical density at 280 nm > 0.2 were combined, exhaustively dialyzed against water and finally freeze dried. The elution pattern of a CB-Sepharose separation as described above is shown in Figure 2. All chromatographic experiments were carried out at a temperature of 4°C.

EXAMPLE II

15 Anti-thrombogenic activity of heparin-albumin conjugates

A heparin-albumin conjugate was prepared using the process described in Example I, starting with non-fractionated heparin.

The conjugate prepared according to Example I was passed over an anti-thrombin III Sepharose-column. The elution pattern of this conjugate showed two fractions (Figure 3); both fractions were measured on thrombin-inactivation (Figure 4) and on factor Xa inactivation (Figure 5). The results show that the several fractions differ in anti-coagulant activity.

Moreover, the conjugate prepared according to Example I, on the basis of both inactivation experiments, was measured and compared with heparin, which was used for the synthesis of the heparin-albumin conjugate. The results thereof in Figure 6 and in Figure 7 show that the conjugate has working properties comparable to those of the heparin that was used for the synthesis of the conjugate.

Claims

1. A process for the preparation of a conjugate of an anticoagulant and a water soluble protein, wherein the process includes coupling said anticoagulant to said protein within an aqueous medium and in the presence of a coupling agent and wherein the improvement comprises providing an anticoagulant-protein conjugate by using a coupling agent that is an amide bond forming agent to form an amide linkage between said anticoagulant and said protein.
2. The process according to claim 1, wherein said anticoagulant-protein conjugate is formed by covalent bonding.
3. The process according to claims 1-2, wherein said amide bond forming agent is 1-ethyl-3-dimethylamino-propyl carbodiimide or a homolog thereof, N-hydroxy succinimide ester or a homolog thereof, or N-ethyl-5-phenyl-isoxazolium-3-sulfonate or a homolog thereof.
4. The process according to any of the preceding claims, wherein said anticoagulant is heparin.
5. The process according to any of the preceding claims, wherein the process includes dissolving said anticoagulant and said protein in water to form a solution, adjusting the pH of the solution to a value not greater than 5.5; adding an aqueous solution of said coupling agent to said solution, said adding step being in incremental batches while maintaining the pH value at not greater than 5.5; agitating the solution while said coupling is proceeding; and recovering the anticoagulant protein conjugate.

6. The process according to claim 5, wherein the pH value is between about 5.0 and 5.5.
7. The process according to any of the preceding
5 claims, further including adjusting the mol ratio of said anticoagulant to said protein by varying the weight of anticoagulant added during the process with respect to the weight of said protein added during the process.
- 10 8. The process according to any of the preceding claims, further including adding an aldehyde to crosslink said protein of the anticoagulant-protein conjugate.
- 15 9. The process according to claim 8, wherein said aldehyde is glutaraldehyde.
10. The process according to any of the preceding claims, wherein said anticoagulant is heparin,
20 and further including fractionating said heparin into heparin fractions by separating same on the basis of differing molecular weights and/or on the basis of differing affinity to anti-thrombin III.
- 25 11. The process according to any of the preceding claims, wherein said water soluble protein is human albumin.
12. The process according to claims 5-11, wherein said
30 recovering step includes passing a mixture including the anticoagulant-protein conjugate, free protein and free anticoagulant over a first sorption agent to thereby sorb the anticoagulant-protein conjugate, free protein and free anticoagulant to the first
35 sorption agent; utilizing an element of increasing ionic strength in order to first elute the free protein and form an anticoagulant-containing eluate


- 42 -

including the anticoagulant-protein conjugate and the free anticoagulant; passing said anticoagulant-containing eluate over a second sorption agent from which the anticoagulant-protein conjugate and the free anticoagulant are separately desorbed in order to isolate the anticoagulant-protein conjugate.

13. The process according to claim 12, wherein said first sorption agent is an anion exchange material, and said first sorption agent is a material having a varying affinity for said anticoagulant-protein conjugate and for said free anticoagulant.
14. A process for the improvement of compatibility between blood and a substrate, the process including coating the substrate with an anticoagulant-containing material, wherein the process comprises adsorbing a protein-anticoagulant conjugate to said substrate, said substrate being a hydrophobic material or a hydrophilic material, and said protein-heparin conjugate is prepared according to the process of any of the preceding claims.
15. The process according to claim 14, wherein the protein of said protein-anticoagulant conjugate is non-crosslinked when adsorbed to said substrate, and the process further includes intermolecular cross-linking of the protein.
16. A process for the improvement of compatibility between blood and a substrate, the process including coating the substrate with an anticoagulant-containing material, wherein the process comprises chemically attaching a protein-anticoagulant conjugate to said substrate, said protein-anticoagulant conjugate having been prepared according to the process of claims 1-13.


17. The process according to claim 16, wherein the protein of said protein-anticoagulant conjugate is non-crosslinked when chemically attached to said substrate, and the process further includes inter-
5 molecular cross-linking of the protein. •
18. A process for the improvement of compatibility between blood and a substrate, the process including coating the substrate with anticoagulant
10 material, wherein the process comprises coating the substrate with a protein component, said protein component being a non-crosslinked protein or a crosslinked protein, wherein said protein component is coupled with anticoagulants by a
15 process according to claims 1-13.
19. An article including a surface having an enhanced blood compatibility coating, wherein the coating is effected from a conjugate of anticoagulant and
20 a water soluble protein, said protein being a non-crosslinked protein or a crosslinked protein, said conjugate having been formed by coupling a protein component and an anticoagulant with an amide bond forming agent by the process according to claims
25 1-13.
20. A conjugate for coating a surface of a medical device to enhance blood compatibility of the surface, said
30 conjugate comprising a protein moiety and an anti-coagulant moiety, which protein moiety and anti-coagulant moiety are covalently bonded by an amide bond forming agent by the process according to claims 1-13.

21. The conjugate of claim 20, wherein said anti-coagulant moiety and said protein moiety are present in the conjugate at a mol ratio of no greater than 3 to 1, respectively.
22. A process for the fractionation of conjugates of heparin and a water soluble protein into fractions by separating same on the basis of differing affinity to anti-thrombin III.
23. A process for the improvement of compatibility between blood and a substrate, the process including coating the substrate with heparinous material, wherein the process comprises covalently linking a protein component being a non crosslinked protein or a crosslinked protein, wherein said protein component is coupled with heparin by a procedure utilizing 1-ethyl-3-dimethylaminopropyl carbodiimide as a coupling agent.
24. The process according to claim 23 wherein said protein component is albumin.
25. A process for the improvement of compatibility between blood and a substrate, the process including coating the substrate with anticoagulant material, wherein the process comprises covalently linking a protein component to a substrate, said protein component being a non cross-linked protein or a crosslinked protein, wherein said protein component is coupled with anticoagulant by a procedure utilizing an amide bond forming agent as a coupling reagent.
26. The process according to claim 25 wherein said protein component is albumin and the anticoagulant is a heparinous material.




ELUTION PROFILE OF Alb-Hep + Hep on Cibacron Blue-Sepharose
 APPLIED ON THIS COLUMN 170 ml of the DEAE column { 280 = 2.94
 Hep = 2.67 mg/ml


FIG. 2





ELUTION PROFILE OF Alb-Hep on ATIII-Sephacrose

FIG. 3










0081853

2 / 2

FX_a INACTIVATION BY AT III CATALYZED BY
Hep (O-O) en Hep-Alb (□-□)

FIG.7

OD 405: THE QUANTITY OF FX_a PRESENT
AFTER REACTION WITH AT III AND HEPARIN



0081853



European Patent
Office

EUROPEAN SEARCH REPORT

Application number

EP 82 11 1637

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 3)
Y	FR-A-2 318 189 (MASSACHUETTS INSTITUTE OF TECHNOLOGY) *Page 10, line 19; claims*	1-26	C 08 B 37/10 C 08 H 1/00 A 61 L 17/00
Y	DE-A-2 720 544 (PHILIP NICOLAS SAWYER) *Claims 1,19*	1-26	
Y	CHEMICAL ABSTRACTS, vol. 77, no. 3, 17th July 1972, page 296, no. 17003r, Columbus Ohio (USA); R.V.YUNUSOV: "Complexing of heparin with plasma proteins". & VOP. MED. KHOM. 1972, 18(2), 189-91. *Abstract*	1	
Y	US-A-4 003 792 (PATRICK JONES HILL et al.) *Examples*	1	TECHNICAL FIELDS SEARCHED (Int. Cl. 3)
A	US-A-3 099 600 (NAZZARENO TOCCACELI)		C 08 B C 08 H A 61 K A 61 L
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 31-03-1983	Examiner LENSEN H.W.M.
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>& : member of the same patent family, corresponding document</p>			